



FEATURE	STANDARD	CRYSTAL
COVERING ADHESION (% particles dragging)	UNE EN ISO 2409:2013	1--2
CRACK RESISTANCE	UNE EN 14323:04	5
SURFACE SOUNDNESS	UNE EN 311:2002	1,2 N/mm <sup>2</sup>
COLD CHECK 30 CYCLES (INITIAL TEMP. 60°)	UNE 48 025:1979	No damage
LIGHT FASTNESS	UNE EN 14323:04	E. grey 4-5
BEHAVIOUR AGAINST DRY HEAT	UNE EN 12722:09+A1:14	5
BEHAVIOUR IMPACT STRESS (LARGE DIAMETER STEEL BALL)	UNE EN 14323:04	200 cm
CHEMICAL STRESS (food, drinks, cleaning products, etc.)	DIN 68 861-1:11	1C
RESISTANCE TO COLD LIQUIDS (coffee, ethanol, sodium carbonate, sodium chloride, tea)	UNE EN 12720:09+A1:14	5
BEHAVIOUR OF MOIST HEAT	UNE EN 12721:09+A1:14	5
BEHAVIOUR AGAINST SCRATCHING	UNE EN 15186:12 (lineal method)	20 N (tread width 0,13mm)
BEHAVIOUR AGAINST CIGARETTE BURNS	UNE EN 14323:04	2
BEHAVIOUR AGAINST WATER VAPOUR	UNE EN 14323:04	4
20 DEGREE GLOSS	UNE EN 14323:04	90 ± 5 GU
COLOUR LIMITS	CIE LabCH D65/10°	ΔE ≤ 0,7

**Transport and handling of material**


- Make sure that the panels do not slide over each other during loading and unloading and transport operations. Lift them by hand or, if possible, by means of a vacuum device.
- Pay particular attention to dirt, foreign bodies and sharp edges that can cause damage in case of rubbing against the surfaces.
- The protective film, must be removed only after processing the panel.

**Storage of material**

- Use a FIFO inventory management method, in order to minimise the mixture of products with different dates of production.
- Store the panels in normal climatic conditions (temperature between 10° and 35° C and 40-65% RH).
- Stack the panels on top of each other on a horizontal flat base: never let the panels stand on the edge.
- The protective film, must never be exposed to direct sunlight or subjected to extreme heat, in order to avoid this, it is recommended to cover the upper panel.

**Cleaning**

- Cleaning with soapy water on a clean soft cloth, is the recommended procedure, in order to avoid chemical components that can damage the surface.

Finish: Gloss	Length: 3.050/2.440mm	Format: Panel	
Thickness: 18mm	Width: 1.220mm	With Film	

